

ALKAMIX™ ADDITIVE MASTERBATCH

ENGINEERING THERMOPLASTIC

ALKAMIX™ IS A REGISTERED TRADEMARK OF MARPLEX AUSTRALIA PTY. LTD.

ALKAMIX™ MB-6007

ALKAMIX™ MB-6007 is a slip masterbatch formulated with slip additive (Oleamide) at a concentration of 1.1 percent.

ALKAMIX™ MB-6007 can be added to polyethylene during extrusion to reduce the coefficient of friction. The level required will vary according to coefficient of friction desired, gauge of film and other factors such as the presence of other additives (including antiblocks, colourants / pigments, etc...).

The maximum level of addition of ALKAMIX™ MB-6007 based on both good manufacturing practice and to ensure conformance to the requirements to the United States Food and Drug Administration Regulations CFR21 is 15 percent when added to a polyethylene formulation free of any slip additives. The suitability of finished articles manufactured using this material as a component, and the observance of given limitations, must be verified by the converter for each application to ensure compliance with all relevant regulations. An overall migration limit may apply to the finished article.

| | <u>CONDITIONS</u> | <u>UNITS</u> | <u>TYPICAL VALUES</u> | <u>TESTING METHODS</u> |
|--------------------------------------|-------------------|-------------------|-----------------------|------------------------|
| <u>1. Physical Properties</u> | | | | |
| Density of Base Resin | | g/cm ³ | 0.920 | ASTM D792 |

All test results were obtained using uncoloured material.

Issued: May 2016

Material Safety Data Sheet (MSDS): Code 30530302

Ixom Operations Pty Ltd makes no representation with regard to the completeness or accuracy of the information and any recommendations contained in this data sheet, and accepts no responsibility for loss or damage whatsoever resulting from the use of, or reliance upon, the information and any recommendation herein. Ixom Operations Pty Ltd products are sold on standard terms and conditions, a copy of which is available on request.

| | | |
|----------------------------------|---|----------------|
| IXOM OPERATIONS PTY LTD | 1 NICHOLSON ST, EAST MELBOURNE, VIC. 3002 AUSTRALIA | |
| | PH: 1300 550 036 FAX: 1300 550 081 | ixom.com |
| CUSTOMER SERVICE: | PH: 1300 557 862 | marplex.com.au |
| MARPLEX AUSTRALIA PTY LTD | 165 FITZGERALD RD, LAVERTON NORTH, VIC. 3026 AUSTRALIA | |
| 24 HR EMERGENCY | • AU 1800 033 111 • NZ 0800 734 607 • INTERNATIONAL +61 3 9663 2130 | |

TYPICAL PROCESSING CONDITIONS

ALKAMIX™ MB-6007

The following typical guidelines are offered as initial processing conditions for **ALKAMIX™ MB-6007**. In practice, processing parameters may need to be varied to give commercially acceptable performance in conjunction with optimum physical properties. For specific technical advice on part design or processing conditions, contact the Marplex Technical Service Department.

Recommended maximum processing temperature 200 °C

Comment(s):

- 1 Cleanliness of the dryer, machine hopper and machine screw/barrel/die head assembly are essential for processing ALKAMIX™ MB-6007 and producing contamination free product.
- 2 ALKAMIX™ MB-6007 is intended for processing with polyethylene and may not be compatible with other polymers
- 3 It is recommended that ALKAMIX™ MB-6007 is purged from the extruder with polyethylene before machine shutdown.

Conversions:

- 1 MPa = 145 psi
- = 10.2 kg/cm²
- = 10 bar
- °C = 5(F-32)/9
- 1 kN/cm² = 0.65 ton/in²