

ProteQ™

POLYPROPYLENE ENGINEERING THERMOPLASTIC

ProteQ™ IS A REGISTERED TRADEMARK OF MARPLEX AUSTRALIA PTY. LTD.

PROTEQ™ C28T2

PROTEQ™ C28T2 is a high flow 10% Talc filled grade of polypropylene copolymer. It is intended for use in applications where a balance of flow and rigidity is required.

Note: The letter U in the product name indicates that UV stabiliser has been added (PROTEQ™ C28UT2)

	<u>CONDITIONS</u>	<u>UNITS</u>	<u>TYPICAL VALUES</u>	<u>TESTING METHODS</u>
<u>1. Mechanical Properties</u>				
Unnotched Izod Impact Strength	12.7 mm x 3.2 mm	J/m	850	ASTM D256
Notched Izod Impact Strength	12.7 mm x 3.2 mm	J/m	60	ASTM D256
Tensile Strength	12.7 mm x 3.2 mm @ 5.0 mm/min	MPa	27	ASTM D638
Elongation to Fail	12.7 mm x 3.2 mm @ 5.0 mm/min	%	100	ASTM D638
Flexural Strength	12.7 mm x 3.2 mm @ 1.3 mm/min	MPa	38	ASTM D790
Flexural Modulus	12.7 mm x 3.2 mm @ 1.3 mm/min	MPa	1800	ASTM D790
<u>2. Thermal Properties</u>				
Heat Deflection Temperature	12.7 mm x 3.2 mm @ 0.455 MPa	°C	125	ASTM D648
	12.7 mm x 3.2 mm @ 1.82 MPa	°C	60	ASTM D648
Coefficient of Linear Thermal Expansion		cm/cm/°C	1.00E-04	ASTM D696
<u>3. Flammability Properties</u>				
UL Flammability	1.6 mm	Rating	HB	UL 94
Glow Wire Temperature	1.6 mm	°C	550	AS/NZS 60695
<u>4. Physical Properties</u>				
Melt Flow Rate	230°C, 2.16 kg	g/10 min	35	ASTM D1238
Shore D Hardness	instantaneous		69	ISO 868
	15 seconds		64	ISO 868
Specific Gravity		-	0.97	ASTM D792
Mould Shrinkage	3.0 mm plaque	%	1.30	ASTM D955

All test results were obtained using uncoloured material.

Issued: May 2016

Material Safety Data Sheet (MSDS): Code 17957

Ixom Operations Pty Ltd makes no representation with regard to the completeness or accuracy of the information and any recommendations contained in this data sheet, and accepts no responsibility for loss or damage whatsoever resulting from the use of, or reliance upon, the information and any recommendation herein. Ixom Operations Pty Ltd products are sold on standard terms and conditions, a copy of which is available on request.

IXOM OPERATIONS PTY LTD 1 NICHOLSON ST, EAST MELBOURNE, VIC. 3002 AUSTRALIA
 PH: 1300 550 036 FAX: 1300 550 081

CUSTOMER SERVICE: PH: 1300 557 862 marplex.com.au

MARPLEX AUSTRALIA PTY LTD 165 FITZGERALD RD, LAVERTON NORTH, VIC. 3026 AUSTRALIA
 24 HR EMERGENCY • AU 1800 033 111 • NZ 0800 734 607 • INTERNATIONAL +61 3 9663 2

TYPICAL PROCESSING CONDITIONS

PROTEQ™ C28T2

The following typical guidelines are offered as initial processing conditions for **PROTEQ™ C28T2**. In practice, processing parameters may need to be varied to give commercially acceptable performance in conjunction with optimum physical properties. For specific technical advice on part design or processing conditions, contact the Marplex Technical Service Department.

Temperature of pellet bed in dehumidifying drier		85 - 90°C
Minimum drying time at desired pellet bed temp		2-4 hours
Mould temperature		50 - 80°C
Nozzle temperature		Do not exceed stock temperature
Melt temperature		220 - 270°C
Cylinder temperatures	Rear	195 - 215°C
	Middle	205 - 225°C
	Front	215 - 235°C
Fill speed		Medium
Screw speed		40 - 60 rpm
Screw back pressure		0.1 - 0.5 MPa
Injection pressure		60 - 140 MPa
Clamp pressure		3 - 6 kN/cm ²

Comment(s):

- 1 Cleanliness of the dryer, machine hopper and machine screw/barrel/nozzle assembly are essential for processing ASTALAC™ ABS and producing contamination free moulded components.
- 2 PROTEQ™ is not compatible with other polymers.
- 3 It is suggested that the pre-drying, moulding die and material temperatures are manually confirmed using a hand held temperature measuring device.

Conversions:

- 1 MPa = 145 psi
- = 10.2 kg/cm²
- = 10 bar
- °C = 5(F-32)/9
- 1 kN/cm² = 0.65 ton/in²